



Base oil (SN-150)

Property	Unit	Test Method	Specification
Appearance	-	Visual	C & B
Color	-	ASTM D-1500	Max 1.5
Density at 15°C	Kg/m ³	ASTM D-4052	880
Kinematic Viscosity at 100°C	mm ² /S(cSt)	ASTM D-445	5 - 5.5
Viscosity Index	-	ASTM D-2270	Min 100
Flash Point	°C	ASTM D-92	Min 200
Pour Point	°C	ASTM D-97	Min -5
Noack at 250°C	Wt%	ASTM D-5800	Max 12
Sulfur	Wt%	-	Max 0.12
TBN-mg KOH/g	-	ASTM D-2896	0.01
TAN-mg KOH/g	-	ASTM D-974	0.01

Head Office Address: Salmandan Alley, Vafamanesh Street, Heravi Square

Phone number:+982121000051-4

  +989120039531

Factories:

1-Isfahan- Razi Industrial Estate

2- Isfahan- Koohpaye Industrial Estate

3-Ghazvin-charmsazi-Pasargad Industrial Estate

4-Tehran-Charm sazi Street-Eshtehard Industrial Estate